

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
17 May 2001 (17.05.2001)

PCT

(10) International Publication Number
WO 01/34713 A1(51) International Patent Classification⁷: C09D 161/06

(21) International Application Number: PCT/KR00/01297

(22) International Filing Date:
13 November 2000 (13.11.2000)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
1999/50110 12 November 1999 (12.11.1999) KR(71) Applicant (for all designated States except US): PO-
HANG IRON & STEEL CO., LTD. [KR/KR]; 1, Koe-
dong-dong, Nam-ku, Pohang-city 790-785, Kyungsang-
buk-do (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): LEE, Jae-Ryung
[KR/KR]; 1, Koedong-dong, Nam-ku, Pohang-shi
790-785, Kyungsangbuk-do (KR). CHANG, Sam-Kyu
[KR/KR]; 1, Koedong-dong, Nam-ku, Pohang-shi790-785, Kyungsangbuk-do (KR). NOH, Sang-Geol
[KR/KR]; 1, Koedong-dong, Nam-ku, Pohang-shi
790-785, Kyungsangbuk-do (KR). CHO, Soo-Hy-
oun [KR/KR]; 1, Koedong-dong, Nam-ku, Pohang-shi
790-785, Kyungsangbuk-do (KR).(74) Agent: KIM, Won-Ho; Teheran Building, 825-33 Yok-
sam-dong, Kangnam-ku, Seoul 135-080 (KR).

(81) Designated States (national): CN, IN, JP, US.

(84) Designated States (regional): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE, TR).


Published:

- With international search report.
- Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: RESIN-COATED STEEL SHEET FOR FUEL TANKS OF AUTOMOBILE AND METHOD OF FABRICATING THE SAME

2-5 μ m	Phenoxy Resin
50mg/m ²	Chromate film
10-40g/m ²	Zn-Ni Plate
	Cold-Rolled steel sheet



(57) Abstract: The present invention relates to a resin-coated steel sheet for fuel tanks of an automobile and a resin solution used for the same. The resin solution of the present invention comprises (a) a main solution of water soluble phenoxy resin having a number average molecular weight of 25,000 to 50,000, (b) 2 to 15 phr of melamine resin on the basis of the main solution, (c) 10 to 20 phr of colloidal silica on the basis of the main solution, and (d) water soluble ethylene-acryl resin containing 50-80 % of ethylene and 50-20 % of acryl resin and having a molecular weight of 20,000 to 50,000, in an amount of 5 to 15 phr on the basis of the main solution; and/or 0.5 to 3.0 phr of phosphoric ester on the basis of the main solution. The resin solution is coated on a cold-rolled steel sheet plated with zinc or zinc alloy over which a chromate layer films, and then dried at a local temperature of 140 to 250 °C to prepare a resin-coated steel sheet for fuel tanks of an automobile.